

# ELASTO LAND PRO MINERAL

Special polymer bitumen membrane (SAP)



## DESCRIPTION

Pre-fabricated waterproofing membrane made of distilled bitumen and special polymers (SAP) having a woven non woven single strand composite polyester reinforcement, which provide the membrane with high mechanical characteristics and excellent dimensional stability. The mineral versions are self-protected on the upper face with mineral slates which reduce superficial heat absorption improving the durability of the membrane. The self-protected versions have a side selvedge of 10 cm and upon request a head selvedge of 15 cm, to improve adhesion between the sheets. The lower face of the membrane is finished with a PE film with striped embossing. The latter has the function of optimizing and maximizing adhesion of the membrane to the laying surface during hot application: respect at a traditional embossing, the surface is more uniform. The thousand lines per square meter operate a uniform marking and close-up of the PE

film thus ensuring a homogeneous opening in the phase of application, obtaining the maximum adhesion to the application plan. Striped embossing facilitates the operator during the flaming because it requires less flame intensity and therefore less absorption of heat from the product itself, eliminating the problems of "Footprints" that occur on the upper face of the both smooth and slated products.

**Reinforcement:** Single strand composite polyester

**Compound:** Special polymer bitumen (SAP)

**Upper finish:** White mineral slates \*

**Lower finish:** PE film

**Intended use:**

**EN 13707 Continuous roofs (certificate no. CE0958-UKCA0120):** Top layer

**EN 13859-1 Under roof tile**

**Application method:** Torch / Mechanical fixing

\* Mineral self-protected products may undergo color tone variations due to the time and length of storage. Exposure to atmospheric conditions, after application, will tend to uniform the color after a few months. The change in color tone cannot therefore be contested and / or complained of as it is a natural phenomenon that the slate manufacturer himself cannot guarantee.

## METHODS OF APPLICATION

For the application of the membrane the use of heat is generally used by means of a gas torch or specific hot air machine. Use protective devices required by law. The application by heat is not suggested when on heat sensitive materials (polystyrene insulation).

- Coordinate the operations in a way to not cause damage to the construction elements and underground structure. Avoid to leave the structure for the night or for periods of prolonged work interruptions without having been properly sealed.
- **The application surface must not have any depressions to avoid the risk of ponding water, the slope must be at least 1.5% on concrete decks and 3% for steel or wooden ones, this to guarantee a proper run off of rainwater.**
- The water drainage spouts should be sufficiently big enough to allow for rain water to be eliminated in an efficient way.
- Prepare cementitious substrates, including verticals and details, with a bituminous primer either by brush or airless, approx. 300/400 g/m<sup>2</sup>.
- Allow this preparation layer to dry before proceeding with any other operation.
- With prefabricated constructions, apply a suitable reinforcing strip along all joints. In the presence of construction joints, prefabricated panels or metal decks, suitable expansion joints are to be considered.
- The membranes must be applied to the substrate fully bonded.
- All details, perimeters, verticals, change of slope as well as projecting area must be fully bonded.

For further information and news it is recommended to consult the NORD BITUMI technical literature; our Technical Office is always available to evaluate particular problems and to provide the necessary assistance to best apply our waterproofing membranes.

# ELASTO LAND PRO MINERAL



Special polymer bitumen membrane (SAP)

## APPLICATION

- On cementitious surfaces and similar apply, by roller or airless, bituminous primer, approx. consumption 300 g/m<sup>2</sup>.
- Apply by torch application a 25 cm strip of membrane reinforced with polyester along all vertical up stands.
- To have all overlaps with the slope, position the membrane always starting from the lowest point, alternating the overlapping areas.
- To facilitate the flow of water towards the drains, so as to encounter as few joints as possible between the sheets, the direction of installation of the membranes must be longitudinal to the direction of the slope of the roof.
- In case of installation of the waterproof sealing element on top of an insulating package, the main direction of the insulating panels must be perpendicular to the direction of installation of the membranes, taking care to install the panels with staggered quincunx combinations.
- Cut the corners of membrane sheet which will be laid under the next sheet at a 45° angle (10x10 cm).
- The joints, both side and head, must be respectively overlapped by 10 & 15 cm.
- The second layer of membrane will be applied astride and over the first one, always in the same direction, and approx. 1/4 of its length from the previous sheet.
- The bituminous membrane will be applied with a propane gas torch to the substrate. It is necessary to heat the entire surface, except for the side & head laps, making sure that the compound forms a liquid mass in front of the roll to assure that it saturates any superficial porosity.
- The side laps (10 cm) and head laps (15 cm) will be heat welded with an appropriate torch; during this stage the overlaps should be pressed by using a roller (15 kg) from which a bead of compound should flow and therefore avoiding to have to iron the overlaps.
- Apply the vertical membrane sheet having the same characteristics of the waterproofing membrane and dimensions equal to the width of the roll, making sure that it overlaps the horizontal one by at least 10 cm, heating it with a gas torch and squeezing it with a trowel until a bead of compound appears from underneath.
- The height of the verticals must be equivalent or superior to the finished surface by at least 15 cm.

## RECOMMENDATIONS

To best use the technical characteristics of bituminous membranes and guarantee the maximum performance and durability of the jobs where they are used, some simple but fundamental rules must be respected.

- The rolls are to be stored in an upright position, indoors in a dry and ventilated area, away from heat sources. Absolutely avoid the stacking of rolls and pallets for storage or transport to avoid possible deformations which may compromise a perfect installation. It is recommended to store the product at temperatures above 0°C.
- The rolls shall be kept in a warm or heated storage area during application, should the workability of the material deteriorate or become stiff and difficult to install during application, these should be returned to the heated storage area and substituted with new rolls. The rolls that are temporarily stored on the roof before application, shall be kept elevated by being left on their own pallets and shall be covered and protected from the weather.
- The application surface must be smooth dry & clean.
- The application surface must be previously treated with a suitable bituminous primer, to eliminate dust and enhance the adhesion of the membrane.
- The application surface must not have any depressions to avoid the risk of ponding water, the slope must be at least 1.5% on concrete decks and 3% for steel or wooden ones, this to guarantee a proper run off of rainwater.
- In situations of application on vertical surfaces superior to 2 meters or on very sloped substrates, apply suitable mechanical fixings to the head laps, after which they will be sealed when torching the head laps.
- The application must be done at temperature higher than +5°C.
- The application must be interrupted in adverse weather conditions (high humidity, rain, etc.).
- The pallets on which the rolls are packaged are intended for normal warehouse use.
- The materials on stock should be rotated following a first in first out rotation.

# ELASTO LAND PRO MINERAL



Special polymer bitumen membrane (SAP)

## TECHNICAL DATA

CHARACTERISTICS	TESTING METHOD	M.U.	TOLERANCE	VALUE
Length/Width	EN 1848-1	m	MLV ≥	10,0 / 1,0
Visible defects	EN 1850-1	visual		None
Mass	EN 1849-1	kg/m <sup>2</sup>	MDV ±10%	4,5
Straightness	EN 1848-1	mm/10 m	MLV	< 20
Watertightness	EN 1928	kPa	MLV ≥	60
External Fire Performance	EN 13501-5			F ROOF
Reaction to fire	EN 13501-1	class		NPD
Maximum tensile strength (L/T)	EN 12311-1	N/50 mm	MDV -20% +50%	700/600
Maximum tensile strength after ageing (L/T)	EN 1296	N/50 mm	MDV -20% +50%	NPD/NPD
Elongation (L/T)	EN 12311-1	%	MDV -15 +30	40/40
Resistance to tearing (L/T)	EN 12310-1	N	MDV -20% +50%	150/150
Dimensional stability	EN 1107-1	%	MLV ≤	0,5
Peel resistance of joints (L/T)	EN 12316-1	N/50 mm	MDV ±20N	NPD/NPD
Cold flexibility	EN 1109	°C	MLV ≤	-15
Cold flexibility after ageing	EN 1296	°C	MDV +15°C	-10
Flow resistance	EN 1110	°C	MLV ≥	110
Flow resistance after ageing	EN 1296	°C	MDV -10°C	110
Joint strength (shear resistance) (L/T)	EN 12317-1	N/50 mm	MDV -20% +50%	600/500
Resistance to impact	EN 12691-B	mm	MLV ≥	1000
Resistance to static loading	EN 12730-A	Kg	MLV ≥	15
Adhesion of granules	EN 12039	%	MLV ≤	30
Root resistance	EN 13948			NPD
Watertightness after ageing	EN 1296	kPa	MLV ≥	60

MDV : value declared by the manufacturer associated with a declared tolerance.

MLV : limit value, minimum or maximum, declared by the manufacturer.

NPD : No Performance Declared in accordance with the EU Construction Products Directive.

## PACKAGING

	ROLL SIZE	WEIGHT KG/M <sup>2</sup>	THICKNESS MM	m <sup>2</sup> PER PALLET
Elasto land Pro Mineral	10 m x 1 m	4,5	-	250

The waterproofing membrane based on distilled bitumen and polymers, as shown in this data sheet does not require the issue of a MSDS, because it does not contain dangerous substances. The information data sheet for the proper use of products is available. The technical data given is based on average values obtained during production. We reserve the rights to change or modify the nominal values without prior notice or advice. The information contained in this data sheet are based on our experience. We cannot take any responsibility for a possible incorrect use of the products. The customer has to choose under their own responsibility a product fit for the intended use.

26/02/2025 - This version supersedes all previous ones.